



Neoprene



Lab & Utility

# NeoTouch<sup>®</sup>

## 25-101 25-201 Neoprene Glove

## A unique combination of allergy prevention and comfort

### FEATURES AND BENEFITS:

#### Reduce the risk of Type I Allergy

With a latex-free formulation, NeoTouch<sup>®</sup> gloves are appropriate for the prevention of Type I allergies.

#### Chemical resistant

They provide excellent resistance to acids, bases and alcohols.

#### Comfort

Thanks to an exclusive formulation, NeoTouch gloves are convincingly the most comfortable synthetic single-use gloves available.

#### Easy Donning

NeoTouch<sup>®</sup> gloves have a polyurethane inner-coating that ensures easy donning.

#### Grip

Their textured fingertips provide a secure grip in both dry and wet conditions.



**Ansell**

## TECHNICAL DATA SHEET:

### PRODUCT INFORMATION:

	25-101	25-201
<b>Material</b>	Neoprene	
<b>Color</b>	Bright Green	
<b>Glove Design</b>	Ambidextrous, Powder Free, Textured Finger	
<b>Cuff</b>	Beaded Cuff	
<b>Audit Standards</b>	ISO 13485	
<b>Quality Control</b>	EN420, EN374/1,2,3, US : FDA 21 CFR 177-2600, ASTM D6977	
<b>Packaging</b>	100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper cartons	
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.	
<b>Country of Origin</b>	Indonesia	

### PHYSICAL PROPERTIES:

	PROPERTY	TYPICAL VALUES					TESTING METHOD
	SIZE	XS 5½-6	S 6½-7	M 7½-8	L 8½-9	XL 9½-10	ASTM D3767/EN 420
Length (mm)	25-101	240	240	240	240	240	
	25-201	290	290	290	290	290	
Average Palm Width (mm)		76	86	95	106	115	

Freedom from Holes (Inspection level I)	1.5 AQL	ASTM D5151/EN 374-2
Palm Thickness Single Wall	(mm:0.13) / (mils:5.1)	ASTM D3767/EN 420

	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength	≥ 14 Mpa	≥ 18 Mpa	ASTM D 412-06a
Elongation at Break (%)	≥ 700	≥ 600	ASTM D 412-06a
Modulus @ 500%	max 2.5	max 3.0	ASTM D 412-06a

### ORDERING INFORMATION:

	SIZE	XS 5½-6	S 6½-7	M 7½-8	L 8½-9	XL 9½-10
25-101	ASPEN US	385727	385728	385729	385730	385731
	ORACLE US	104978	104979	104980	104981	104982
	ASPEN (Other)	NA	588441	588442	588443	588444
25-201	ASPEN	385683	385679	385680	385681	385682
	ORACLE	NA	104973	104974	104975	104976



For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

North America, Latin America and Caribbean: +1800 800 0444

Asia Pacific: +852 2185 0600

Europe: +32 2 528 74 00

Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.

