



Neoprene



Clean
Environment

DermaShield[®]

73-721

Clean Neoprene Glove

The most advanced glove solution in allergy prevention

FEATURES AND BENEFITS:

Low Allergenicity

Made from a proprietary Poly-chloroprene blend and free of latex proteins and accelerators. It is the ideal choice in the prevention of both Type I and Type IV allergies associated with Natural Rubber Latex and accelerators.

Chemical Protection

Neoprene composition offers chemical resistance to a broad spectrum of chemicals.

No Cuff Roll-Down

Ansell SureFit Technology eliminates “cuff roll down”. By maintaining the glove securely around the arm, Sure Fit Technology provides workers in Life Sciences with more protection during routine lab work and manufacturing by ensuring the efficacy of the gloves as a barrier protection.

Cleanroom Compatibility

Clean and sterile and ideally suited for ISO class 5 (class 100) environments.



TECHNICAL DATA SHEET:

PRODUCT INFORMATION:

Material	Neoprene
Color	Green
Glove Design	Hand specific, Powder Free, Smooth Grip
Cuff	Beaded Cuff
Clean Room Compatibility	All packaging is printed with cleanroom-compatible IPA-resistant ink. The gloves are triple-bagged for superior contamination control. Recommended for ISO 5 areas.
Audit Standards	ISO 9001 : 2008
Quality Control	Freedom from holes G1 AQL 0.65
Packaging	20 right and left hand gloves are packed in separate compartments in an easy-to-open polybag with perforated line opening; 1 polybag per vacuum sealed polybag; 2 polybags per vacuum sealed master polybag, 5 master polybags per case liner; 200 pairs per carton.
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country of Origin	Sri Lanka

PHYSICAL PROPERTIES:

PROPERTY	TYPICAL VALUES							TESTING METHOD
SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0	
Length (mm)	310	310	310	310	310	310	310	ASTM D3767/EN 420
Average Palm Width (mm)	78	84	91	97	104	112	116	
Freedom from Holes (Inspection level I)	0.65 AQL							ASTM D5151/EN 374-2
Palm Thickness Single Wall	(mm:0.175) / (mils:6.9)							ASTM D3767/EN 420
Particle Count	2300 particles/cm2							IEST-RP-CC005.2-7
	BEFORE AGING			AFTER AGING				
Ultimate Tensile Strength	23 Mpa			20 Mpa				ASTM D 412-06a
Elongation at Break (%)	1000			824				ASTM D 412-06a
Modulus @ 500%	2,4			3,6				ASTM D 412-06a
Force at break (N)	16			15				EN 455-2

ORDERING INFORMATION:

SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0
ASPEN	388897	388898	388899	388900	388901	388902	388903



EN 374



EN 374



EN 421



CE 0493

For additional information visit us at www.ansell.com, or call us at

North America, Latin America and Caribbean: +1800 800 0444

Asia Pacific: +852 2185 0600

Europe: +32 2 528 74 00

Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.