



Natural  
Rubber Latex



Sterile  
Environment

# AccuTech<sup>®</sup>

## 91-250

### Sterile Natural Rubber Latex Glove

## Setting the standard for comfort and quality

### FEATURES AND BENEFITS:

#### Great Comfort

Designed with a specific formulation of latex that provides increased flexibility and elasticity. The glove's thinner fingertips, combined with the bisque finish, provide greater sensitivity, increased handling precision and dexterity.

#### Nice Fit

The cuff is slightly thicker, nicely fitting over the garment for better safety of the wearer

#### Ease of donning

Designed with an inner silicone coating that facilitates easy donning and double-gloving.



**Ansell**

### TECHNICAL DATA SHEET:

#### PRODUCT INFORMATION:

<b>Material</b>	Natural Rubber Latex
<b>Color</b>	Natural Color
<b>Glove Design</b>	Hand-specific, Powder Free, Textured Grip
<b>Cuff</b>	Straight
<b>Sterilization</b>	Cobalt 60, minimum 25kGy, SAL 10 <sup>-6</sup>
<b>Clean Room Compatibility</b>	All packaging is printed with cleanroom-compatible IPA-resistant ink. The gloves are triple-bagged for superior contamination control. The polybags have an easy-tear opening. Recommended for ISO 5 areas.
<b>Audit Standards</b>	ISO 9001, ISO 13485, CE Mark & ISO 11137
<b>Quality Control</b>	AQL - Before packing: GII, AQL 0.65 (Water Leak Test), Final Release: GI AQL 1.0 (Water Leak Test)
<b>Packaging</b>	The glove is packaged one pair per poly wallet, sealed in a poly envelope; 10 pairs per sealed polybag; 5 sealed polybags per master polybag; 4 master polybags per lined carton; 200 pairs per carton.
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
<b>Country of Origin</b>	Malaysia

#### PHYSICAL PROPERTIES:

PROPERTY	TYPICAL VALUES							TESTING METHOD
	6.0	6.5	7.0	7.5	8.0	8.5	9.0	
SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0	ASTM D3767/EN 420
Length (mm)	285	285	285	285	285	285	285	
Average Palm Width (mm)	80	85	90	95	100	110	115	
Freedom from Holes (Inspection level I)	0.65 AQL							ASTM D5151/EN 374-2
Palm Thickness Single Wall	(mm: 0.18) / (mils: 7)							ASTM D3767/EN 420
Particle Count	3500 particles/cm <sup>2</sup>							IEST-RP-CC005.2-7
Endotoxin	< 20 EU/pair of gloves							ASTM D7102
	BEFORE AGING			AFTER AGING				
Ultimate Tensile Strength	26 Mpa			20 Mpa				ASTM D 412-06a
Elongation at Break (%)	820			810				ASTM D 412-06a
Modulus @ 500%	3,5			NA				ASTM D 412-06a
Force at break (N)	18			17				EN 455-2

#### ORDERING INFORMATION:

SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0
ASPEN	385950	385951	385952	385953	385954	385955	385956



CE 0493

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at  
 North America, Latin America and Caribbean: +1800 800 0444  
 Asia Pacific: +852 2185 0600  
 Europe: +32 2 528 74 00  
 Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.

