



Nitrile



Lab & Utility

# TouchNTuff®

ADVANCED PRODUCT & WORKER PROTECTION

## 92-600 92-605 Nitrile Glove

## Proven splash resistance against hazardous chemicals

### FEATURES AND BENEFITS:

#### Outstanding Chemical Resistance

Further testing of the TouchNTuff® by a certified body on an even wider range of chemicals confirms that it resists a greater variety of industrial chemicals for longer periods than any other nitrile disposable gloves.

#### Excellent puncture resistance

Manufactured from nitrile, TouchNTuff® offers up to four times the puncture resistance of comparable natural rubber latex, and three times the resistance of similar neoprene gloves.

#### Prevention from Type I Allergy

It contains no natural rubber latex proteins, which prevents from Type I allergies for the wearer. Primary skin irritation studies and Insult Patch tests have also shown no evidence of risk from irritation or allergic contact dermatitis.

#### Easy Donning and Strong Grip

With a unique “Thin Nitrile Technology” formulation, this glove offers easy donning and strong grip in wet or dry conditions. The glove is highly versatile and suitable for many different uses.



### TECHNICAL DATA SHEET:

#### PRODUCT INFORMATION:

	92-600	92-605
<b>Material</b>	Nitrile	
<b>Color</b>	Green	
<b>Glove Design</b>	Ambidextrous, Powder Free, Smooth Grip	Ambidextrous, Powder Free, Textured Fingers
<b>Cuff</b>	Beaded Cuff	
<b>Audit Standards</b>	ISO 9001	
<b>Quality Control</b>	EN420, EN374/1,2,3, ASTM D 6319, FDA 21 CFR 177-2600, Arrete 09/11/04, European Regulation 1935/2004, German Recommendation for Food Commodities.	
<b>Packaging</b>	100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper cartons	
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.	
<b>Country of Origin</b>	Sri Lanka	Thailand

#### PHYSICAL PROPERTIES:

PROPERTY	TYPICAL VALUES				TESTING METHOD	
SIZE	S 6½-7	M 7½-8	L 8½-9	XL 9½-10		
Length (mm)	92-600	240	240	240	ASTM D3767/EN 420	
	92-605	300	300	300		
Average Palm Width (mm)	92-600	85	96	105		
	92-605	82	90	99		
Freedom from Holes (Inspection level I)	92-600	All regions except North and South America 1.5 AQL North and South America 4.0 AQL				ASTM D5151/EN 374-2
	92-605	1.5 AQL All regions				
Palm Thickness Single Wall	(mm : 0.12) / (mils : 4.7)				ASTM D3767/EN 420	
	<b>BEFORE AGING</b>		<b>AFTER AGING</b>			
Ultimate Tensile Strength	> 14 Mpa		> 14 Mpa		ASTM D 412-06a	
Elongation at Break (%)	> 500		> 400		ASTM D 412-06a	
Force at break (N)	> 6		> 6		EN 455-2	

#### ORDERING INFORMATION:

	SIZE	S 6½-7	M 7½-8	L 8½-9	XL 9½-10
92-600	ASPEN US	552822	552823	552824	552825
	ORACLE US	105077	105018	105079	105080
	ASPEN OTHERS	552942	552943	552944	522945
92-605	ASPEN	588104	588105	588106	588107

(All regions except North & South America)

#### 92-600



#### 92-605



For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at  
 North America, Latin America and Caribbean: +1800 800 0444  
 Asia Pacific: +852 2185 0600  
 Europe: +32 2 528 74 00  
 Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2015 All Rights Reserved.